
















Classification	Method	FLORAFLOOR C403
Type of floor covering	EN ISO 10582 (EN 649)	Compact heterogeneous floor covering
European classification	EN ISO 10874 (EN 685)	23 - 31
Reaction to fire	EN 13501-1	B _{fl-s1} 
Technical characteristics	Method	
Plank size / Form of delivery	 EN ISO 24342 (EN 427)	1 220,0 x 183,0 mm / 9 planks per box = 2,00 m ²
Surface treatment	—	PUR
Total thickness	 EN ISO 24346 (EN 428)	4,00 mm
Wear layer thickness	 EN ISO 20340 (EN 429)	0,30 mm
Total weight	 EN ISO 23997 (EN 430)	7,44 kg/m ²
Technical performances	Method	
Dimensional stability to heat	 EN ISO 23999 (EN 434)	≤ 0,25 %
Residual indentation	 EN ISO 24343-1 (EN 433)	≤ 0,10 mm
Furniture leg resistance	 EN 424	No damage
Castor chair resistance	 ISO 4918 (EN 425)	No damage
Impact sound reduction	 EN ISO 717-2	ΔL _w = 3 dB
Walk impact noise	 NF S 31-074	Class C
Colour fastness	 EN ISO 105-B02	≥ 6
Thermal resistance	 EN ISO 10456	0,05 m ² .K/W (suitable for underfloor heating - max 27°C)
Wear resistance	 EN 660	Group T
Slip resistance	 EN 13893	DS (≥ 0,30)
Warranty of use		15 years



EN 14041 : 2005
DOP-004-2016-07

Edition 10/2016